



As talked in TEM Lab(II), an edge-on orientation of phase boundaries (GBs) is important to "see" GBs in TEM correctly. Here are two HRTEM examples of an amorphous GB in silicon nitride (a), and a layer of calcium cation segregation at a twin GB in alumina. Today we will see similar phenomena in SEM diffractions with different specimen orientations.